

Larsen Building Products Ltd

n5Plus



## dry4 Screed

By Larsen Building Products Ltd

### Detailed description

Factory controlled pre-blended floor screed comprising of specially selected graded aggregates, fibres and proprietary hydraulic binder to give a rapid drying, shrinkage controlled semi-dry floor screed. It is ideal for use in all instances in place of traditional semi-dry screed, i.e. unbonded, bonded or floating constructions; standard or heated screeds. dry4 Screed eliminates inconsistencies associated with site batching to provide a floor screed of uniform quality.

### Product guidance - As Standard

Screed properties:

- Form: Granular powder.
- Colour: Grey.
- Mix proportions: 1.6–1.8 L water: 25 kg dry4 screed.
- Bed thickness (minimum/ maximum): 20/ 150 mm (bonded).
- Application temperature: + 5–30°C.
- Light traffic: 12 hours.
- Compressive strength: 30 MPa (after twenty eight days).
- Drying time to covering: 4 days @ 50mm

### Options

dry4 Binder:

Hydraulic binder which when mixed with sand will give a rapid drying, shrinkage controlled semi-dry floor screed. The resulting screed is ideal for use in all instances in place of traditional semidry screed, i.e. unbonded, bonded or floating constructions; standard or heated screeds. dry4 Binder improves the quality, strength and drying speed of the screed over standard cement screeds.

- Form: Powder.
- Colour: Grey.
- Mix proportions: 20 kg binder: 110–140 kg sand: 10–12 L water.
- Bed thickness (minimum/ maximum): 20/ 150 mm (bonded).
- Application temperature: + 5–30°C.
- Light traffic: 12 hours.
- Compressive strength: 20 MPa (after seven days).

## Product specification

### Manufacturer

- Name: Larsen Building Products Ltd  
- Web: [www.larsenbuildingproducts.com](http://www.larsenbuildingproducts.com)  
- Email: [joris@larsenbuildingproducts.com](mailto:joris@larsenbuildingproducts.com)

Product reference dry4 Screed

Binder Not required  
Required